



UNIFLEX ACRYLIC ROOF COATING SYSTEM GUIDE FOR SINGLE PLY RESTORATION

MATERIAL REFERENCE GUIDE

***** Reference full System Guide Specifications for Single Ply Restoration *****

COMPONENTS

Acrylic Roof Coating:

1. Uniflex® 41-300 WHITE acrylic [SMIS#992-1156]
2. Uniflex® 41-321 SPE GRAY acrylic [SMIS#992-1206]

Primers:

1. Uniflex® Bond-it Wash 38-620 (required for EPDM) [SMIS#992-1115]

Sealant:

1. Uniflex One Flash Sealant 51-920 Gray [SMIS#6510-38820]

Application of Roof Coating:

1. Apply Uniflex 41-321 SPE Gray Elastomeric to entire roof surface at a rate of one and a half (1.5) gallons per square [Twenty-Four (24) wet mils; Twelve (12) mils DFT]. Allow 24 hrs. to cure.
2. Apply Finish Coat of Uniflex® 41-300 Premium Elastomeric (41-300)
 - a. Ten (10) year UNIGUARD Warranty: Apply one (1) layer of primary roof coating at one and a half (1.5) gallons per square [Twenty-four (24) wet mils; Twelve (12) mils DFT].
 - b. Fifteen (15) year UNIGUARD Warranty: Apply two (2) layers of primary roof coating at a total of two and a half (2.5) gallons per square [Forty (40) wet mils; Twenty (20) mils DFT].

[please visit www.uniflexroof.com for additional system warranty information]

Uniflex is not responsible for specific building designs by others, for deficiencies in construction, installation or workmanship unless specifically stated. Uniflex does not provide services for quality control of workmanship. In the event the project requires audit and/or inspection of workmanship, it is suggested to contact an independent consultant or 3rd party firm to discuss quality control services.

