



## SECTION 07500

### UNIFLEX SILICONE ROOF COATING SYSTEM GUIDE FOR ASPHALTIC RESTORATION

#### MATERIAL REFERENCE GUIDE

\*\*\*\*\* Reference full System Guide Specifications for Asphaltic Membranes \*\*\*\*\*

#### COMPONENTS

Silicone Roof Coating:

1. Uniflex® 44-600 WHITE silicone [SMIS#6511-79442]
2. Uniflex® 44-320 GRAY silicone (optional) [SMIS#6509-63069]

Sealant:

1. Uniflex Silicone Flashing Sealant 44-900 White [SMIS#6509-71252]
2. Uniflex One Flash Sealant 51-920 Gray [SMIS#6510-38820]

#### Application of Roof Coating:

##### Smooth BUR/Smooth Modified

1. Ten (10) year UNIGUARDWarranty:  
Apply one (1) layer of primary roof coating at two (1.5) gallons per square [Twenty-four (24) wet mils; Twenty-two (22) mils DFT].

##### Granular Modified

1. Ten (10) year UNIGUARDWarranty:  
Apply one (1) layer of primary roof coating at two (2) gallons per square [Thirty-two (32) wet mils; Thirty (30) mils DFT].

[\[please visit www.uniflexroof.com for additional system warranty information\]](http://www.uniflexroof.com)

*Uniflex is not responsible for specific building designs by others, for deficiencies in construction, installation or workmanship unless specifically stated. Uniflex does not provide services for quality control of workmanship. In the event the project requires audit and/or inspection of workmanship, it is suggested to contact an independent consultant or 3rd party firm to discuss quality control services.*

