



Uniflex Urethane Snapshot

Single Ply- EPDM, TPO, PVC



P
R
E
P
A
R
E

Conduct: Moisture Survey & Adhesion Tests
Repair: Open Seams, Flashings, Damaged Membrane
Replace: Wet Insulation, Pitch Pan Sealants, Termination Sealants
Clean: Pressure Wash- EPDM requires Bond-it Wash Primer
Detail: With Urethane88 Gray basecoat 46-620
Apply: Uniflex Urethane88 Gray basecoat 46-620 to entire roof surface
Apply: Uniflex Urethane88 White 46-600 finish coat

A
P
P
L
Y

Detail: Detail all flashings and penetrations. Apply 46-620 base at 16 wet mils, extending 2 inches on each side of the overlap seams.

Basecoat: Apply Uniflex Urethane88 Gray basecoat 46-620 to entire roof surface at 22 wet mils

Finishcoat
10 Year System: Apply Uniflex Urethane88 White at 22 wet mils
15 Year System: Apply 2 coats of Uniflex Urethane88 White at 22 wet mils per coat
20 Year System: Apply 3 coats of Uniflex Urethane88 White at 22 wet mils per coat

W
A
R
R
A
N
T
Y



Ten or Fifteen Year Available

No Cost or Pre-Approval Required

Pre-Approval Required- Warranty Fee Required

Ten, Fifteen or Twenty Year Available

L
I
N
K
S

Uniflex Website
Uniflex Warranty
Full Specification
Roof Calculator

P
R
O
D
U
C
T
S

Uniflex Urethane88 Gray Basecoat
Uniflex Urethane88 White Finish
Uniflex Bond-it Wash Primer



Need a Moisture Survey?

Ask Your Uniflex Regional Manager about Uniflex Roof View Thermal Imaging
or click the image for additional information

NOTE: This Snapshot is not designed to replace the full system specification. Full specifications are available at www.uniflexroof.com/specifications. Contractor must be a Uniflex Approved Applicator for System Warranties.