



Uniflex Acrylic Snapshot

Modified Bitumen



P R E P A R E	Conduct:	Moisture Survey & Adhesion Tests
	Repair:	Open Seams, Flashings, Damaged Membrane (Lap Sealant)
	Replace:	Wet Insulation, Pitch Pan Sealants, Termination Sealants
	Clean:	Pressure Wash
	Detail:	Uniflex One Flash
	Apply:	Uniflex MB Primer 41-512 Gray
	Apply:	Uniflex Premium 41-300 Finish-coat

A P P L Y	OneFlash:	<i>Detail all flashings and penetrations. Apply OneFlash at 60 wet mils, extending 2 inches on each side of the overlap seams.</i>
	Basecoat:	<i>Apply Uniflex MB Acrylic Gray Primer at 1.0 gallons per square. (16 wet mils) over field seams. Apply Uniflex MB Acrylic Gray Primer at 1.5 gallons per square. (24 wet mils) over roof field.</i>
	Finishcoat	<i>10 Year System: Apply Uniflex Premium 41-300 at a total rate of 1.5 gallons per square. (24 wet mils) 15 Year System: Apply Uniflex Premium 41-300 at a total rate of 2.0 gallons per square. (32 wet mils)</i>

W A R R A N T Y		UNIGUARD™ Materials Warranty	Ten or Fifteen Year Available
		UNIGUARD™ Systems Warranty	No Cost or Pre-Approval Required
			Pre-Approval Required- Warranty Fee Required
			Ten or Fifteen Year Available

L I N K S	Uniflex Website	P R O D U C T S	Uniflex 41-300 Premium White Finish Coat
	Uniflex Warranty		Uniflex MB Gray Acrylic Basecoat
	Full Specification		Uniflex One Flash
	Roof Calculator		Uniflex MS Hybrid Lap Sealant



Need a Moisture Survey?

**Ask Your Uniflex Regional Manager about Uniflex Roof View Thermal Imaging
or Click the Image for more information**

NOTE: This Snapshot is not designed to replace the full system specification. Full specifications are available at www.uniflexroof.com/specifications. Contractor must be a Uniflex Approved Applicator for System Warranties.